

Supplementary Information

**Three-dimensional nanoframes with dual rims as
nanoprobes for biosensing**

Hajir Hilal^{a†}, Qiang Zhao^{a†}, Jeongwon Kim^a, Sungwoo Lee^a, MohammadNavid Haddadnezhad^a,
Sungjae Yoo^a, Soohyun Lee^a, Woongkyu Park^b, Woocheol Park^a, Jaewon Lee^a, Joong Wook Lee^c,
Insub Jung^{a,d*} and Sungho Park^{a*}

^aDepartment of Chemistry, Sungkyunkwan University (SKKU), Suwon 16419, Republic of Korea

^bMedical & Bio Photonics Research Center, Korea Photonics Technology Institute (KOPTI), Gwangju, 61007, Republic of Korea

^cDepartment of Physics and Optoelectronics Convergence Research Center, Chonnam National University, Gwangju 61186, Republic of Korea

^dDepartment of Chemistry and Institute of Basic Science, Sungkyunkwan University (SKKU), Suwon 16419, Republic of Korea

e-mail: insub.jung@skku.edu; spark72@skku.edu

†: these authors contributed equally

Table of contents

Supplementary Figure 1. Selective Pt deposition and etching of inner Au. FE-SEM images of (a) Au octahedral NPs, (b) Au@Pt NPs, and (c) Pt octahedral mono-rim NFs. (d) Corresponding UV-Vis-NIR spectra.	4
Supplementary Figure 2. The effect of Ag precursors during the well-faceted growth of Au octahedral mono-rim NFs. (a-c) FE-SEM images of Au octahedral mono-rim NFs with different gap distances as the amount of Au increases under the presence of Ag ions (well-faceted growth) and (d) corresponding UV-vis-NIR spectra with sequential blue-shifts of plasmonic bands from 854 to 762 to 700 nm. (e-g) FE-SEM images of Au octahedral tip-blobbed NFs with increasing Au ions without Ag ions and (f) corresponding UV-vis-NIR spectra with plasmonic blue-shifting from 870 to 724 to 636 nm.....	5
Supplementary Figure 3. Growth pattern control of Au on the 3D PtAu skeleton. (a) FE-SEM images of different Au growth patterns on the 3D PtAu skeletons with different halide ions and pH of the reaction solution under the presence of Ag ⁺ . (b) Summarized experimental conditions for growth pattern control of Au. Depending on counter anions, Au mono-rim NFs with rough surface, smooth surface, or well-faceted sharp surfaces.	6
Supplementary Figure 4. Controlling the amount of the Ag⁺ with regard to Au³⁺ during the reactions. FE-SEM images of Au mono-rim NFs with different [Ag ⁺]/[Au ³⁺] ratios of (a) 0.05 (b) 0.1 (c) 1. A red box indicates the successful case of well-faceted growth of Au mono-rim NFs. All scale bars = 100 nm.	7
Supplementary Figure 5. Growth evolution of Pt dual-rim NFs starting from Au mono-rim NFs with a round tip or smooth surfaces. FE-SEM images of (a) Au round-tip NFs, (b) after the second Pt rim-on deposition, (c) Pt dual-rim NFs after the selective inner Au etching, and (d) UV-vis-NIR spectra that correspond to panel a (black line), b (red line) and c (blue line). (e) When we use Au mono-rim NFs with smooth surfaces as initial templates, (f) Pt is not preferentially deposited along the edges, leading to (g) dull-like Pt dual-rim NFs. (h) UV-vis-NIR spectra that correspond to e (black line), f (red line) and g (blue line).	8
Supplementary Figure 6. HADDF-STEM EDS elemental analysis of Au dual-rim NFs. The spectrum reveals the compositions (Au, Ag, Pt) of Au octahedral dual-rim NFs. The atomic percentage of Au octahedral dual-rim NFs are Ag (10.04 %), Au (75.79 %), and Pt (14.18 %), respectively.....	9
Supplementary Figure 7. Calculated optical extinction of Au dual-rim NFs under an electric field with different oscillating field directions. Simulated absorption, scattering, and extinction spectra under an electric field of light oscillating along the (a) z-axis and (b) y-axis.	10
Supplementary Figure 8. Dark-field spectra of Au dual-rim NFs. We obtained dark-field scattering spectra of individual single Au dual-rim NFs and observed that the scattering bands were centered around 695 nm to 720 nm. Inset shows an optical image and each number indicate single Au dual-rim NFs. The scale bar in the inset denotes 1 μm.	11
Supplementary Figure 9. Control of the gap distances between the inner and outer rims of Pt octahedral dual-rim NFs. (a, d, g) Well-faceted Au octahedral mono-rim NFs with different rim thicknesses. (b, e, h) Pt@Au@Pt octahedral NFs after selective Pt deposition along the edges of Au mono-rim NFs. (c) Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel a and b, respectively. A blue line corresponds to Fig. 2h in the main text. (f) Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel d and e, respectively. A blue line corresponds to Fig. 2g in the	


main text. **(i)** Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel **g** and **h**, respectively. A blue line corresponds to Fig. 2f in the main text. All scale bars = 100 nm..... 12

Supplementary Figure 10. Control of the gap distances between the inner and outer rims in Au octahedral dual-rim NFs. **(a)** Pt dual-rim NFs with a gap size of 17 nm. **(b-d)** Au octahedral dual-rim NFs with different gap distances from 14 nm to 5 nm, controlled by the amount of Au³⁺ added to the reaction solutions. The cartoons represent the size information of each nanostructure, and the numbers denote the sizes in nm. **(e)** UV-vis-NIR spectra of Au dual-rim NFs with different gap sizes. The error bars represent standard deviations from 30 particles. 13


Supplementary Figure 11. An FE-SEM image and UV-vis spectrum for the Au mono-rim NFs. **(a)** An UV-vis-NIR spectrum and **(b)** an FE-SEM image of Au octahedral mono-rim NFs. **(c, d)** Single-particle SERS measurements of 10 individual Au octahedral mono-rim NFs..... 14

Supplementary Figure 12. Liquid SERS measurements. **(a)** A schematic illustration of liquid SERS measurements. **(b)** Raman spectra of Au dual-rim NFs toward 2-NTT in solution phase. Only 3D Au dual-rim NFs show Raman signals of 2-NTT. **(c)** SERS spectra of Au dual-rim NFs dispersed in solution (n = 30), demonstrating high reproducibility. 15


Supplementary Figure 13. An FE-SEM image of 2D Au triangular dual-rim NFs. The size of 2D Au triangular dual-rim NFs (97±4 nm) is selected to be comparable to the outer diameter of 3D Au dual-rim NFs (93±3 nm). The synthesis method for 2D Au triangular dual-rim NFs can be found in the previous literature.¹..... 16




Supplementary Figure 1. Selective Pt deposition and etching of inner Au. FE-SEM images of **(a)** Au octahedral NPs, **(b)** Au@Pt NPs, and **(c)** Pt octahedral mono-rim NFs. **(d)** Corresponding UV-Vis-NIR spectra.




Supplementary Figure 2. The effect of Ag precursors during the well-faceted growth of Au octahedral mono-rim NFs. (a-c) FE-SEM images of Au octahedral mono-rim NFs with different gap distances as the amount of Au increases under the presence of Ag ions (well-faceted growth) and **(d)** corresponding UV-vis-NIR spectra with sequential blue-shifts of plasmonic bands from 854 to 762 to 700 nm. **(e-g)** FE-SEM images of Au octahedral tip-blobbed NFs with increasing Au ions without Ag ions and **(f)** corresponding UV-vis-NIR spectra with plasmonic blue-shifting from 870 to 724 to 636 nm.




Supplementary Figure 3. Growth pattern control of Au on the 3D PtAu skeleton. (a) FE-SEM images of different Au growth patterns on the 3D PtAu skeletons with different halide ions and pH of the reaction solution under the presence of Ag⁺. **(b)** Summarized experimental conditions for growth pattern control of Au. Depending on counter anions, Au mono-rim NFs with rough surface, smooth surface, or well-faceted sharp surfaces.




Supplementary Figure 4. Controlling the amount of the Ag^+ with regard to Au^{3+} during the reactions. FE-SEM images of Au mono-rim NFs with different $[\text{Ag}^+]/[\text{Au}^{3+}]$ ratios of (a) 0.05 (b) 0.1 (c) 1. A red box indicates the successful case of well-faceted growth of Au mono-rim NFs. All scale bars = 100 nm.




Supplementary Figure 5. Growth evolution of Pt dual-rim NFs starting from Au mono-rim NFs with a round tip or smooth surfaces. FE-SEM images of **(a)** Au round-tip NFs, **(b)** after the second Pt rim-on deposition, **(c)** Pt dual-rim NFs after the selective inner Au etching, and **(d)** UV-vis-NIR spectra that correspond to panel **a** (black line), **b** (red line) and **c** (blue line). **(e)** When we use Au mono-rim NFs with smooth surfaces as initial templates, **(f)** Pt is not preferentially deposited along the edges, leading to **(g)** dull-like Pt dual-rim NFs. **(h)** UV-vis-NIR spectra that correspond to **e** (black line), **f** (red line) and **g** (blue line).




Supplementary Figure 6. HADDF-STEM EDS elemental analysis of Au dual-rim NFs. The spectrum reveals the compositions (Au, Ag, Pt) of Au octahedral dual-rim NFs. The atomic percentage of Au octahedral dual-rim NFs are Ag (10.04 %), Au (75.79 %), and Pt (14.18 %), respectively.




Supplementary Figure 7. Calculated optical extinction of Au dual-rim NFs under an electric field with different oscillating field directions. Simulated absorption, scattering, and extinction spectra under an electric field of light oscillating along the **(a)** z-axis and **(b)** y-axis.




Supplementary Figure 8. Dark-field spectra of Au dual-rim NFs. We obtained dark-field scattering spectra of individual single Au dual-rim NFs and observed that the scattering bands were centered around 695 nm to 720 nm. Inset shows an optical image and each number indicate single Au dual-rim NFs. The scale bar in the inset denotes 1 μm .




Supplementary Figure 9. Control of the gap distances between the inner and outer rims of Pt octahedral dual-rim NFs. (a, d, g) Well-faceted Au octahedral mono-rim NFs with different rim thicknesses. (b, e, h) Pt@Au@Pt octahedral NFs after selective Pt deposition along the edges of Au mono-rim NFs. (c) Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel **a and **b**, respectively. A blue line corresponds to Fig. 2h in the main text. (f) Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel **d** and **e**, respectively. A blue line corresponds to Fig. 2g in the main text. (i) Corresponding UV-vis-NIR spectra. Black and red lines correspond to panel **g** and **h**, respectively. A blue line corresponds to Fig. 2f in the main text. All scale bars = 100 nm.**




Supplementary Figure 10. Control of the gap distances between the inner and outer rims in Au octahedral dual-rim NFs. (a) Pt dual-rim NFs with a gap size of 17 nm. (b-d) Au octahedral dual-rim NFs with different gap distances from 14 nm to 5 nm, controlled by the amount of Au^{3+} added to the reaction solutions. The cartoons represent the size information of each nanostructure, and the numbers denote the sizes in nm. (e) UV-vis-NIR spectra of Au dual-rim NFs with different gap sizes. The error bars represent standard deviations from 30 particles.



Supplementary Figure 11. An FE-SEM image and UV-vis spectrum for the Au mono-rim NFs. (a) An UV-vis-NIR spectrum and **(b)** an FE-SEM image of Au octahedral mono-rim NFs. **(c, d)** Single-particle SERS measurements of 10 individual Au octahedral mono-rim NFs.



Supplementary Figure 12. Liquid SERS measurements. (a) A schematic illustration of liquid SERS measurements. (b) Raman spectra of Au dual-rim NFs toward 2-NTT in solution phase. Only 3D Au dual-rim NFs show Raman signals of 2-NTT. (c) SERS spectra of Au dual-rim NFs dispersed in solution ($n = 30$), demonstrating high reproducibility.



Supplementary Figure 13. An FE-SEM image of 2D Au triangular dual-rim NFs. The size of 2D Au triangular dual-rim NFs (97 ± 4 nm) is selected to be comparable to the outer diameter of 3D Au dual-rim NFs (93 ± 3 nm). The synthesis method for 2D Au triangular dual-rim NFs can be found in the previous literature.¹

Supplementary References

1. Go S, *et al.* Ring-in-a-Triangle Nanoframes: Integrating with Intra- and Interhotspots for Highly Amplified Near-Field Focusing. *Nano Letters* **22**, 1734-1740 (2022).