

Supplementary Information for

Erosion-inhibiting potential of stannous fluoride-enriched CPP-ACP complex *in vitro*

Deena Al Saady¹, Colin Hall², Suzanne Edwards³, Eric C. Reynolds⁴, Lindsay C. Richards¹, Sarbin Ranjitkar^{1,*}

¹Adelaide Dental School, University of Adelaide, Adelaide, Australia

*Email: sarbin.ranjitkar@adelaide.edu.au

²Future Industries Institute, University of South Australia, Mawson Lakes, Australia

³Adelaide Health Technology Assessment (AHTA), School of Public Health, University of Adelaide, Adelaide, Australia

⁴Oral Health Cooperative Research Centre, Melbourne Dental School, Bio21 Institute, The University of Melbourne, Melbourne, Victoria, Australia

<u>Group</u>	<u>Baseline (S0)</u>		<u>Stage 1 (S1)</u>		<u>Stage 2 (S2)</u>		<u>Stage 3 (S3)</u>	
	Mean	SD	Mean	SD	Mean	SD	Mean	SD
<u>Erosion depth</u>								
G1	2395.5	1089.7	2421.8	1091.8	2457.3	1091.5	2526.6	1104.7
G2	1877.0	1086.5	1899.3	1088.8	1930.0	1092.3	1960.8	1097.3
G3	1491.2	810.6	1499.3	810.2	1513.7	810.7	1530.0	810.9
G0	1416.4	945.2	1485.8	964.3	1668.8	995.7	1934.4	1032.0
<u>Scratch depth</u>								
G1	76.5	14.4	89.7	16.2	215.3	49.6	387.7	54.1
G2	115.0	30.8	130.8	29.5	283.8	47.5	435.9	91.8
G3	66.2	12.0	70.5	11.6	89.1	14.1	107.6	23.3
G0	72.6	14.9	102.0	15.6	279.6	50.6	522.4	121.5

Abbreviations: SD = standard deviation; G1 (Group 1) = Erosion + CPP-ACP in saliva; G2 (Group 2) = Erosion + SnF₂ in saliva; G3 (Group 3) = Erosion + SnF₂/CPP-ACP in saliva; G0 (Control group) = Erosion + saliva

Table S1. Erosion depth (nm) and scratch depth (nm) data at baseline (S0) and subsequent stages (S1, 1 min; S2, 5 min; and S3, 10 min of erosion) that were analyzed by using linear mixed-effects models, controlling for baseline. The changes from baseline for erosion depth are shown in Fig. 1, and for scratch depth in Fig. 2.