



Chi:TPP

(A)



Chi:DS

(B)



(C)

|            | Diameter (nm)    | Hydralazine encapsulation (%) | Zeta potential (mV) |
|------------|------------------|-------------------------------|---------------------|
| Chi-TPP    | $277.4 \pm 43.1$ |                               | $10.78 \pm 1.54$    |
| Chi-DS     | $294.2 \pm 57.8$ |                               | $-7.16 \pm 3.69$    |
| Chi-TPP/Hy | $307.6 \pm 28.9$ | 15.8                          | $14.51 \pm 2.58$    |
| Chi-DS/Hy  | $338.1 \pm 34.5$ | 23.5                          | $-4.84 \pm 1.38$    |