




Blend code	MFI (g/10 min)
PP ₁	1.53 ± 0.01
PP ₂	1.70 ± 0.01
PP ₃	2.67 ± 0.06
PP ₄	1.74 ± 0.02
PP ₅	2.57 ± 0.06
PP ₆	1.86 ± 0.01
PP ₇	2.08 ± 0.02
PP ₈	2.12 ± 0.01
d ₂ w [®]	41.8 ± 0.1
POM	7.39 ± 0.01