

	Contact angle (degree)		
	Fine group	Coarse group	P-value
Oxinium	73.9 (5.6) ^{b,d,e}	76.3(9.2) ^{b,c,d,e}	0.33
Co-Cr-Mo	104.1 (5.7) ^{a,c,d,e}	105.8 (1.0) ^{a,c,d,e}	0.06
Ti-6Al-4V	77.0 (5.3) ^{b,d,e}	84.7 (3.0) ^{a,b,e}	0.002
Cp-Ti	89.2 (7.1) ^{a,b,c}	84.8 (3.0) ^{a,b}	0.20
SUS316L	90.0 (2.3) ^{a,b,c}	91.2 (2.0) ^{a,b,c}	0.39

Table 2