

Technical Data Sheet

Lupolen 2420H



Low Density Polyethylene

Product Description

Lupolen 2420 H is a non-additivated, low density polyethylene. It is characterized by a good balance between processability and mechanical properties. Films made from *Lupolen 2420 H* exhibit good optical properties. It is delivered in pellet form.

This product is not intended for use in medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see *Lupolen 2420H* [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Europe
Application	Bags & Pouches; Food Packaging Film; Hygiene Film; Liner Film; Shrink Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film
Attribute	General Purpose; Good Heat Seal; Good Optical Properties; Good Processability

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	1.9	g/10 min	ISO 1133-1
Density	0.924	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	260	MPa	ISO 527-1, -2
Tensile Stress at Yield	11	MPa	ISO 527-1, -2
Film			
Dart Drop Impact Strength, F50	110	g	ASTM D1709
Tensile Strength			
MD	25	MPa	ISO 527-1, -3
TD	21	MPa	ISO 527-1, -3
Tensile Strain at Break			
MD	250	%	ISO 527-1, -3
TD	600	%	ISO 527-1, -3
Coefficient of Friction	>0.8		ISO 8295
Impact			
Failure Energy	4	J/mm	DIN 53373
Thermal			
Vicat Softening Temperature, (A/50 N)	94	°C	ISO 306
Peak Melting Point	111	°C	ISO 3146

Optical		
Haze, (50 µm)	<8 %	ASTM D1003
Gloss		
(20°)	>50	ASTM D2457
(60°)	>100	ASTM D2457
Additional Information		
Test Specimen	Film	
Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 180°C and a blow-up ratio of 2.5:1.		
Processing Parameters		
Extrusion Temperature	160-200 °C	

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.

Further Information

Health and Safety:

The resin is manufactured to the highest standards, but special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off-line operations. The products of degradation may have an unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention should be observed.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

Recycled resins may have previously been used as packaging for, or may have otherwise been in contact with, hazardous goods. Converters are responsible for taking all necessary precautions to ensure that recycled resins are safe for continued use.

For further information about safety in handling and processing please refer to the Safety Data Sheet.

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks.

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

Users should review the applicable Safety Data Sheet before handling the product.

This product(s) may not be used in the manufacture of any of the following, without prior written approval by Seller for each specific product and application:

- (i) U.S. FDA Class I or II Medical Devices; Health Canada Class I, II or III Medical Devices; European Union Class I or II Medical Devices;
- (ii) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices;
- (iii) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration;
- (iv) tobacco related products and applications, electronic cigarettes and similar devices.
- (v) safety components in automotive applications, for example: air bags, air bag unit housings and covers, seat belt mechanisms, brake systems, pedals and pedal supports, steering systems.

The product(s) may not be used in:

- (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- (ii) applications involving permanent implantation into the body;
- (iii) life-sustaining medical applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

In addition to the above, LyondellBasell may further prohibit or restrict the use of its products in certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Glacido, Hifax, Hiflex, Histif, Hostacom, Hostalen, Hyperzone, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.



Product Information

Biodegradable Polymers

Version 1.0

June 2016

G-PMS/B

ecoflex[®] F Blend C1200

Certified compostable polyester for compostable film

® = ecoflex is a registered trademarks of BASF SE;
Lupolen is a registered trademark of
Lyondell Basell group companies

Product description

ecoflex[®] F Blend C1200 is our biodegradable, statistical, aliphatic-aromatic copolyester based on the monomers 1,4-butanediol, adipic acid and terephthalic acid in the polymer chain. ecoflex[®] F Blend C1200 will biodegrade to the basic monomers 1,4-butanediol, adipic acid and terephthalic acid and eventually to carbon dioxide, water and biomass when metabolized in the soil or compost under standard conditions.

ecoflex[®] F Blend C1200 has properties similar to PE-LD because of its high molecular weight and its long chain branched molecular structure.

- Transparent to translucent, semi-crystalline structure with DSC melting point in the range of PE-LD: 110 - 120°C
- High ultimate elongation at break and high failure energy (dart drop)
- High, but controllable water vapour transmission rate (WVTR)
- MVR (190°C, 2.16 kg): 2.5 - 4.5 ml/10 min
- Good thermostability up to 230°C
- regular predrying of pellets
- Good processability on blown film lines
- Down gaging to 10 µm possible
- Weldable and printable

ecoflex® F Blend C1200 fulfils the requirements of the European standard DIN EN 13432, the US standard ASTM D 6400 and the Japanese GreenPla standard for compostable and biodegradable polymers, because it can be degraded by micro-organisms. The biodegradation process in soil depends on the specific environment (climate, soil quality, population of micro-organisms).

ecoflex® F Blend C1200 is one of the few biodegradable plastics, which complies in its composition with the European and American food stuff legislation for food contact: EU Directive 2002/72/EC (as amended) and US food contact notification FCN 907. Specific limitations and more details are given on request. The converter or packer has to check the suitability of the article for the application.

Form supplied and storage

ecoflex® F Blend C1200 is supplied as lens shaped pellets in 1 t big bags or bulk containers. Temperatures during transportation and storage may not exceed 70°C at any time. Storage time of unopened bags may not surpass 12 month at room temperature (23°C).

Quality Control

ecoflex® F Blend C1200 is produced as a standard material in a continuous production process according to DIN EN ISO 9001:2000. The melt volume rate, MVR, at 190°C, 2.16 kg, according to ISO 1133 has been defined as specified parameter for quality control. A certificate can be provided with each lot number (10 t) upon request. In order to obtain a high accuracy for the MVR measurement the granules should be dried for 30 minutes at 70°C using e. g. an electronic moisture analyser (e. g. Brabender Aquatrac plus). Other data given in our literature are typical values, which are not part of our product specification for ecoflex® F Blend C1200.

Applications

ecoflex® F Blend C1200 has been developed for the conversion to flexible films using a blown film or cast film process. Typical applications are packaging films, agricultural films and compost bags. In view of numerous factors influencing functionality and shelf life of ecoflex® films and finished articles made thereof these parameters have to be tested by the converters before utilisation.

We supply technical service information concerning the blown or cast film process with ecoflex® F Blend C1200 on demand.

Intellectual Property

It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Some uses of ecoflex® and product obtained by use of ecoflex® are subject of intellectual property rights. Purchase of ecoflex® does not entitle the buyer or any third to produce, offer or use any blends of ecoflex® protected under property rights and all their equivalents as listed here:

- EP-B 1656423
- EP-B 937120
- EP-B 950689
- EP-B 1838784
- EP-B 947559
- EP-B 965615
- EP-B 2707427

Typical basic material properties of ecoflex® F Blend C1200

Property	Unit	Test Method	ecoflex® F Blend C1200	Lupolen® 2420 F
Mass density	g/cm³	ISO 1183	1.25 - 1.27	0.924
Melt flow rate MFR 190°C, 2.16 kg	g/10 min	ISO 1133	2.7 - 4.9	0.6 - 0.9
Melt volume rate MVR 190°C, 2.16 kg	ml/10 min	ISO 1133	2.5 - 4.5	0.8 - 1.2
Melting point	°C	DSC	110 - 120	111
Shore D hardness	–	ISO 868	32	48
Vicat VST A/50	°C	ISO 306	91	96

Typical properties of ecoflex® F Blend C1200 blown film, 50 µm

Property	Unit	Test Method	ecoflex® F Blend C1200	Lupolen® 2420 F
Transparency	%	ASTM D 1003	82	89
Tensile strength	N/mm²	ISO 527	35/44	26/20
Ultimate strength	N/mm²	ISO 527	36/45	–
Ultimate Elongation	%	ISO 527	560/710	300/600
Failure Energy (Dyna Test)	J/mm	ISO 53373	24	5.5
Permeation rates:				
Oxygen (23°C, dry)	cm³/(m²·d·bar)	ASTM D 3985	1200	2900
Water vapour (23°C, 85% r.h.)	[g/(m²·d)]	ASTM F-1249	135	1.7

Note

The information submitted in this document is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance for a special purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Ingeo™ Biopolymer 7001D Technical Data Sheet

Injection Stretch Blow Molded Bottles

Ingeo biopolymer 7001D, a NatureWorks LLC product, is a thermoplastic resin derived from annually renewable resources and is specifically designed for use in injection stretch blow molded (ISBM) bottle applications. Ingeo biopolymer 7001D can be run using conventional ISBM equipment, but processes at lower temperatures than PET and can attain good resolution of mold detail on conventional tooling.

Applications

Injection stretch blow molded (ISBM) bottles for single- or two- stage operations. Potential applications for Ingeo 7001D include:

- Fresh Dairy
- Edible Oils
- Fresh Water
- Health/Beauty/Amenity

Preform Design & Injection Molding

Preform design is critical in making a container with good clarity and physical properties. Designing a preform for use in an Ingeo bottle is, to an extent, specific to the blow mold equipment, bottle design, and mold tooling. As a starting point, designing a preform with an areal (axial x hoop) stretch ratio (SR) of 8-11, an axial SR of 2-3, and a hoop SR of 3-4, should allow for the blow molding of the desired container. A preform designed with a thinner end cap might also be desired in order to prevent excess material accumulating in the base of the blown container. Preform designs with shorter, uniform, and less abrupt transitions may also help to control bottle material distribution.

Injection Molding of Preforms

A general-purpose screw designed to minimize residence time and shear is recommended. A screw designed for PET is a relatively good choice, as they are a low compression screw that minimizes shear. Processing conditions should be controlled accordingly in order to minimize melt temperature and residence time. The shot size and hot runner capacity should be sized accordingly to the extrusion barrel size. This helps to maintain a short barrel residence time and eliminate the chance of material degradation. It is important to avoid prolonged exposure to shear or heat, in order to prevent polymer degradation.

Typical Material & Application Properties¹

Physical Properties		Ingeo 7001D	ASTM Method
Specific Gravity		1.24	D792
MFR, g/10 min (210°C, 2.16kg)		6	D1238
Glass Transition Temperature		55-60°C	D3418
Crystalline Melt Temperature		145-160°C	D3418
Transmission Rates	Oxygen	675 cc-mil/m ² -24hr-atm	D1434
	Carbon Dioxide	2,850 cc-mil/ m ² -24hr-atm	Internal
	Water Vapor	375 g-mil/ m ² -24hr	F1249
Clarity		Transparent	
General Blow Molding Guidelines ²			
Preform Temperature		80-100°C (176-212°F)	
Stretch Rod Speed		1.2-2 m/sec	
Mold Temperature		21-38°C (70-100°F)	

(1) Typical properties; not to be construed as specifications.

(2) Typical conditions; an experimental approach may be required.

Re-Heating of Preforms

The heating of the preforms is critical in getting a container with good clarity and material distribution. Typical preform temperatures for running on a two-stage process are approximately 80-100°C. This temperature range may be lower or higher depending on the preform design, bottle design, and re-heating equipment that are being used. The use of a reheat additive may also be desired to help with heat penetration through the preform body, especially with thicker designs or when being run on machines with short oven lengths.

Reheat-Stretch-Blow Molding

Preforms made out of Ingeo biopolymer can be run on both single and two-stage conventional blow molding equipment. Ingeo biopolymer has a lower extensional viscosity than PET, and so is easier to stretch. The use of pre-blow pressure and timing are important control parameters to help manage material distribution throughout the bottle. The base of any given bottle may have thicker material distribution than the sidewall. This thick area in the bottle base needs to be distributed well and cooled quickly.

This helps keep the base from deforming because the material is still warm in this area. Depending on the application and bottle design, a base design that includes ribs and a high pushup for reinforcement may be desired.

Ingeo Biopolymer 7001D Technical Data Sheet

Process Details

Startup and Shutdown*

Ingeo biopolymer is not compatible with a wide variety of resins, and special purging sequences should be followed:

1. At normal operating temperatures for the current polymer in the injection molder, purge with polypropylene (PP), preferably starting with a low MI (high viscosity) PP, switching to a high MI (low viscosity) PP.
2. Bring injection molder to steady state at normal operating temperatures for Ingeo PLA while running PP.
3. Vacuum out dryer, hopper system, hoses, valves, and any other potential points where contamination could occur. Dry Ingeo resin according to recommending drying conditions & times. Ingeo resin needs to be dried before thermal processing/extrusion.
4. Introduce Ingeo resin into the injection molder at the recommended operating temperatures. (See operating temperatures listed.)
5. It will be obvious when pure Ingeo is being extruded, as it gives a clear, steady melt.
6. At shutdown, purge machine with a high-viscosity resin, such as PP.

Note: If transitioning from PET to Ingeo biopolymer, it is advised to first transition from these materials to a low melt index (higher viscosity), PP. Follow this transition to a higher MI (lower viscosity) PP. All PET polymers must be cleaned and expelled from vessels and the extrusion system before Ingeo is introduced. Next, lower temperatures to recommended starting conditions for Ingeo before continuing the startup process.

Drying

In-line drying capabilities are essential to process Ingeo biopolymer 7001D, which is supplied with moisture content of less than 0.04% (400 ppm). The recommended moisture content to prevent viscosity degradation and possible lactide reformation is less than 0.010% (100 ppm). Typical drying conditions are 4-6 hours at 149-185°F (65-85°C) with desiccated air, a dew point of -40°F (-40°C), and an airflow rate of greater than 0.5 cfm/lbs of pellets. The resin should not be exposed to atmospheric conditions after drying. Transfer lines and hoppers should be sealed or padded with inert gas. Keep resin package sealed until ready to use and promptly reseal packages of unused material. See our NatureWorks LLC 'Crystallizing and

Typical Processing Parameters*

Parameter	Units (English)	Units (Metric)
Melt Temperature	390-430°F	200-220°C
Feed Throat	70°F	20°C
Feed Section	355°F	180°C
Compression Section	410°F	210°C
Metering Section	410-430°F	210-220°C
Nozzle	410-430°F	210-220°C
Mold	70-100°F	
Back Pressure	100-200psi	
Mold Shrinkage	0.004 in/in. +/- .001	

*These are starting points and may need to be optimized. It is important to optimize back-pressure, process temperature, mold temperature, and injection speed such that the cycle time and the internal stresses in the finished part are kept to a minimum. This will help keep the shrinkage of the preform upon re-heating to the lowest level possible while keeping preform production as high as possible. Using a hot runner system in the injection-molding step is also recommended to help keep shear stress and preform shrinkage to a minimum.

Drying' guide for more information. Before introducing Ingeo biopolymer into any vessel, the vessel should be clean and free of any cross-polymer contamination.

Food Packaging Status

U.S. Status

On January 3, 2002 FCN 000178 submitted by NatureWorks LLC to FDA became effective. This effective notification is part of list currently maintained on FDA's website at

<http://www.fda.gov/food/ingredientspackaginglabeling/packagingfcs/notifications/default.htm>

This grade of Ingeo biopolymer may therefore be used in food packaging materials and, as such, is a permitted component of such materials pursuant to section 201(s) of the Federal, Drug, and Cosmetic Act, and Parts 182, 184, and 186 of the Food Additive Regulations. All additives and adjuncts contained in the referenced Ingeo biopolymer formulation meet the applicable sections of the Federal Food, Drug, and Cosmetic Act. The finished polymer is approved for all food types and B-H use conditions. We urge all of our customers to perform GMP (Good Manufacturing Procedures) when constructing a package so that it is suitable for the end use.

European Status

This grade of Ingeo biopolymer complies with Plastics Regulation 10/2011 as amended. No SML's for the above referenced grade exist in Plastics Regulation 10/2011 as amended. NatureWorks LLC would like to draw your attention to the fact that the EU- Plastics Regulation 10/2011, which applies to all EU-Member States, includes a limit of 10 mg/dm² of the overall migration from finished plastic articles into food. In accordance with Plastics Regulation 10/2011 the migration should be measured on finished articles placed into contact with the foodstuff or

Ingeo Biopolymer 7001D Technical Data Sheet

appropriate food simulants for a period and at a temperature which are chosen by reference to the contact conditions in actual use, according to the rules laid down in Plastics Regulation 10/2011.

Please note that it is the responsibility of both the manufacturers of finished food contact articles as well as the industrial food packers to make sure that these articles in their actual use are in compliance with the imposed specific and overall migration requirements.

This grade as supplied meets European Parliament and Council Directive 94/62/EC of 20 December 1994 on packaging and packaging waste heavy metal content as described in Article 11.

Should you need further clarification, please do not hesitate to contact NatureWorks LLC.

Bulk Storage Recommendations

The resin silos recommended and used by NatureWorks LLC are designed to maintain dry air in the silo and to be isolated from the outside air. This design would be in contrast to an open, vented to atmosphere system that we understand to be a typical polystyrene resin silo. Key features that are added to a typical (example: polystyrene) resin silo to achieve this objective include a cyclone and rotary valve loading system and some pressure vessel relief valves. The dry air put to the system is sized to the resin flow rate out of the silo. Not too much dry air would be needed and there may be excess instrument air (-30°F dew point) available in the plant to meet the needs for dry air. Our estimate is 10 scfm for a 20,000 lb/hr rate resin usage. Typically, resin manufacturers specify aluminum or stainless steel silos for their own use and avoid epoxy-lined steel.

Safety and Handling Considerations

Safety Data Sheets (SDS) for Ingeo biopolymers are available from NatureWorks. SDS's are provided to help customers satisfy their own handling, safety, and disposal needs, and those that may be required by locally applicable health and safety regulations. SDS's are updated regularly; therefore, please request and review the most current SDS's before handling or using any product.

The following comments apply only to Ingeo biopolymers; additives and processing aids used in fabrication and other materials used in finishing steps have their own safe-use profile and must be investigated separately.

Hazards and Handling Precautions

Ingeo biopolymers have a very low degree of toxicity and, under normal conditions of use, should pose no unusual problems from incidental ingestion or eye and skin contact. However, caution is advised when handling, storing, using, or disposing of these resins, and good housekeeping and controlling of dusts are necessary for safe handling of product. Pellets or beads may present a slipping hazard.

No other precautions other than clean, body-covering clothing should be needed for handling Ingeo biopolymers. Use gloves with insulation for thermal protection when exposure to the melt is localized. Workers should be protected from the possibility of contact with molten resin during fabrication.

Handling and fabrication of resins can result in the generation of vapors and dusts that may cause irritation to eyes and the upper respiratory tract. In dusty atmospheres, use an approved dust respirator.

Good general ventilation of the polymer processing area is recommended. At temperatures exceeding the polymer melt temperature (typically 175°C), polymer can release fumes, which may contain fragments of the polymer, creating a potential to irritate eyes and mucous membranes. Good general ventilation should be sufficient for most conditions. Local exhaust ventilation is recommended for melt operations. Use safety glasses (or goggles) to prevent exposure to particles, which could cause mechanical injury to the eye. If vapor exposure causes eye discomfort, improve localized fume exhausting methods or use a full-face respirator.

The primary thermal decomposition product of PLA is acetaldehyde, a material also produced during the thermal degradation of PET. Thermal decomposition products also include carbon monoxide and hexanal, all of which exist as gases at normal room conditions. These species are highly

flammable, easily ignited by spark or flame, and can also auto ignite. For polyesters such as PLA, thermal decomposition producing flammable vapors containing acetaldehyde and carbon monoxide can occur in almost any process equipment maintaining PLA at high temperature over longer residence times than typically experienced in extruders, fiber spinning lines, injection molding machines, accumulators, pipe lines and adapters. As a rough guideline based upon some practical experience, significant decomposition of PLA will occur if polymer residues are held at temperatures above the melting point for prolonged periods, e.g., in excess of 24 hours at 175°C, although this will vary significantly with temperature.

Combustibility

Ingeo biopolymers will burn. Clear to white smoke is produced when product burns. Toxic fumes are released under conditions of incomplete combustion. Do not permit dust to accumulate. Dust layers can be ignited by spontaneous combustion or other ignition sources. When suspended in air, dust can pose an explosion hazard. Firefighters should wear positive-pressure, self-contained breathing apparatuses and full protective equipment. Water or water fog is the preferred extinguishing medium. Foam, alcohol-resistant foam, carbon dioxide or dry chemicals may also be used. Soak thoroughly with water to cool and prevent re-ignition.

Disposal

DO NOT DUMP INTO ANY SEWERS, ON THE GROUND, OR INTO ANY BODY OF WATER. For unused or uncontaminated material, the preferred option is to recycle into the process otherwise, send to an incinerator or other thermal destruction device. For used or contaminated material, the disposal options remain the same, although additional evaluation is required. Disposal must be in compliance with Federal, State/Provincial, and local laws and regulations.

Environmental Concerns

Generally speaking, lost pellets, while undesirable, are benign in terms of their physical environmental impact, but if ingested by wildlife, they may mechanically cause adverse effects. Spills should be minimized, and they should be cleaned up when they happen. Plastics should not be discarded into the environment.

Product Stewardship

NatureWorks has a fundamental duty to all those that use our products, and for the environment in which we live. This duty is the basis for our Product Stewardship philosophy, by which we assess the health and environmental information on our products and their intended use, and then take

Ingeo Biopolymer 7001D Technical Data Sheet

appropriate steps to protect the environment and the health of our employees and the public.

Customer Notice

NatureWorks encourages its customers and potential users of its products to review their applications from the

standpoint of human health and environmental quality. To help ensure our products are not used in ways for which they were not intended or tested, our personnel will assist customers in dealing with ecological and product safety considerations. Your sales representative can arrange the proper contacts. NatureWorks literature should be consulted prior to the use of the company's products.

NOTICE:

No freedom from infringement of any patent owned by NatureWorks LLC or others is to be inferred. No information in this publication can be considered a suggestion to infringe patents.

The technical information, recommendations and other statements contained in this document are based upon tests or experience that NatureWorks believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond NatureWorks control can affect the use and performance of a NatureWorks product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge or control, it is essential that the user evaluate the NatureWorks product to determine whether it is fit for a particular purpose and suitable for the user's method of application. In addition, because use conditions are outside of NatureWorks control and applicable laws may differ from one location to another and may change with time, Customer is solely responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace, use and disposal practices are in compliance with applicable laws and regulations. NatureWorks LLC assumes no obligation or liability for the information in this document.

NATUREWORKS MAKES NO WARRANTY, EXPRESS OR IMPLIED, REGARDING THE INFORMATION CONTAINED HEREIN OR ITS PRODUCTS, INCLUDING BUT NOT LIMITED TO ANY WARRANTY AS TO ACCURACY OR COMPLETENESS OF INFORMATION, OR ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

NOTICE REGARDING PROHIBITED USE RESTRICTIONS: Unless specifically agreed to in writing by NatureWorks, NatureWorks LLC will not knowingly sell or sample any product into any of the following commercial or developmental applications (i) components of or packaging for tobacco products, (ii) components of products intended for human or animal consumption, (iii) any application that is intended for any internal contact with human body fluids or body tissues, (iv) as a critical component in any medical device that supports or sustains human life, (v) in any product that is designed specifically for ingestion or internal use by pregnant women, (vi) in any application designed specifically to promote or interfere with human reproduction, (vii) in microbeads, including those used in personal care/cosmetic applications, or (viii) to manufacture bottles or bottle pre-forms in North America.

For additional information please contact NatureWorks via our [website](#) on the tab called [FAQ's](#) or by clicking [here](#).



15305 Minnetonka Blvd., Minnetonka, MN 55345